

Transmissive Materials for 1μm Optics

		BK7	Fused Silica	MS ZnS	ZnSe
Mechanical Properties	Density (g/cm ³)	2.51	2.203	4.09	5.27
	Poisson's Ratio	0.208	0.17	0.27	0.28
	Hardness (Knoop)	610	500	150-165	105-120
	Rupture Modulus (dyne/cm ²)	1.65E+08	5.00E+09	6.90E+08	5.50E+08
	Young's Modulus (dyne/cm ²)	8.2E+11	7.3E+11	7.45E+11	6.72E+11
Thermal Properties	Linear Expansion Coef (x10 ⁻⁶ /°C)	7.1	0.55	6.5	7.57
	Specific Heat (J/g/°C)	0.858	0.703	0.527	0.356
	Thermal Conductivity (W/cm/°C)	0.0111	0.0138	0.272	0.18
Optical Properties	Scatter Coefficient at 1.06 μm (/cm)	ND	ND	< 3%	< 0.5%
	Scatter Coefficient at 0.6328 μm (/cm)	ND	ND	< 10%	< 3%
	Index of Refraction @ 1.06 μm	1.5066	1.4496	2.287	2.483
	Temp. Change of Refractive Index(x10 ⁻⁶ /°C) @ 1.06 μm	1.2	11	42	70
	Bulk Absorption (/cm) @ 1.07 μm	~ 0.001	~ 0.0001	< 0.0005	< 0.001
	K-Values For Lenses, Plano/Convex Lens	0.07112	0.08994	0.02888	0.02849
	Positive Meniscus Lens	0.06573	0.07792	0.02051	0.01758
Equi-Convex Lens	0.10290	0.11542	0.05494	0.05164	

Zinc sulfide MultiSpectral (ZnS MS) is the only material for NIR and IR freeform optics.

- Notes: 1) ND means not detectable.
 2) K values are used to estimate focus spot size of lenses with spherical aberrations. Below are two equations used to estimate spot size. The equation on the left assumes a perfect lens such as an aspheric lens. The equation on the right assumes the lens has some spherical aberration.

Diffraction Limited Equation

$$d_d = \frac{4 \cdot \lambda \cdot M2 \cdot f}{\pi \cdot d_0}$$

Aberration Limited Equation

$$d_s = \frac{4 \cdot \lambda \cdot M2 \cdot f}{\pi \cdot d_0} + \frac{k \cdot d_0^3}{f^2}$$

Where:

- d_d = diffraction limited focused beam diameter
 d_s = aberration limited focused beam diameter
 λ = wavelength of light
 M2 = mode quality factor for the laser beam

- d₀ = beam diameter at the e⁻² power points
 f = is the focal length of the lens
 k = is the aberration coefficient



INFRARED

...the world leader in CO₂ laser optics

WORLDWIDE SALES OFFICES

To place an order, contact a II-VI sales representative at any of the following locations, or log onto www.iiviinfrared.com/contact for our most complete and up-to-date information.

II-VI INFRARED

375 SAXONBURG BLVD
SAXONBURG, PA 16056
UNITED STATES

888.558.1504 (toll-free in USA)
724.352.1504 (phone)
724.352.4980 (fax)
info@iiviinfrared.com (e-mail)

II-VI WEST

36570 BRIGGS ROAD
MURRIETA, CA 92563
UNITED STATES

800.262.5273 (toll-free in USA)
951.926.7640 (phone)
951.926.1984 (fax)
info@iiviinfrared.com (e-mail)

II-VI BELGIUM NV

BAAIKENSSTRAAT 21/2
B-9240 ZELE
BELGIUM

32 (0) 52 45 86 10 (phone)
32 (0) 52 45 86 11 (fax)
sales@ii-vi.be (e-mail)

II-VI DEUTSCHLAND GmbH

IM TIEFEN SEE 58
D-64293 DARMSTADT
GERMANY

49 6151 880 629 (phone)
49 6151 896 667 (fax)
info@ii-vi.de (e-mail)

II-VI SUISSE S.a.r.l.

MOULIN-DU-CHOC
1122 ROMANEL-SUR-MORGES
SWITZERLAND

41 21 869 02 52 (phone)
41 21 869 93 08 (fax)
info@ii-vi-suisse.ch (e-mail)

II-VI UK LTD.

21 BURLEY ROAD
OAKHAM, RUTLAND
LE15 6DH
ENGLAND

44 1572 771 778 (phone)
44 1572 771 779 (fax)
salesii-vi@oakham.uk.com (e-mail)

II-VI JAPAN

WBG MARIVE EAST 17F
2-6 NAKASE, MIHAMA-KU
CHIBA-SHI, CHIBA 261-7117
JAPAN

81 43297 2693 (phone)
81 43297 3003 (fax)
center@ii-vi.co.jp (e-mail)

II-VI SINGAPORE PTE., LTD.

BLK. 5012, TECH PLACE II
#04-07 & 05-07/12
ANG MO KIO AVE. 5
SINGAPORE 569876

65 6481 8215 (phone)
65 6481 8702 (fax)
info@ii-vi.com.sg (e-mail)

II-VI OPTICS (SUZHOU) CO., LTD.

NO 12, SUTONG ROAD
SUZHOU INDUSTRIAL PARK
SUZHOU, CHINA 215021

86 512 6761 9295 (phone)
86 512 6761 5049 (fax)
twosix@ii-vi.com.cn (e-mail)

www.iiviinfrared.com

